

Safety Coat

Safety Coat Hygienic

Safety Coat Coarse

A two part epoxy with pre-blended aggregate for an even, easy clean, fine, anti slip finish

Watco Safety Coat has been re-formulated to produce a 'Best in Class' water based, anti slip epoxy resin.








This tough, easy to use coating now dries faster to reduce downtime and lasts longer to save recoating costs. The rapid drying formula also allows the application of 2 coats in one day. Our unique blend of the best resins available provides an attractive, low maintenance, hard wearing floor finish which lasts and lasts.

Hygienic grades incorporate Silver Ion technology and are ideal for areas where slip resistance, cleanliness and hygiene are as important as a hard wearing finish.

All grades now carry CE Mark EN1504-2 and have impressive test results for slip resistance, abrasion, scratch and impact resistance, as well as for adhesion, hardness and flexibility. They are also breathable, chemical resistant, safe for food production areas and have a Class 1 fire rating. The range carries an A+ VOC emissions rating with a low level of VOC.

All tests have been undertaken to ISO standard where applicable and demonstrated this 'Best Ever Formulation' to be 40% harder wearing than previously.

Colours/RAL Reference

 Light Grey 0007500	 Mid Grey 7036	 Dark Grey 7005	 Blue Grey 7000
 Black 9005	 Mid Blue 5015	 Dark Blue 5005	 Mid Green 6002
 Signal Red 3020	 Hazard Yellow 1021	 White 9010	
 Tile Red	 Stone 7032		



Samples are available on request. While great care is taken with the colour samples shown, no guarantee can be given that they represent exactly the colours offered.



Areas of use:

- Warehouses
- Production Areas
- Workshops
- Showrooms
- Potentially slippery, heavy wear areas

Features:

- Tough, hard wearing floor finish for heavy wear areas
- Pre-blended aggregate provides an evenly textured finish
- Apply to bare or previously painted surfaces
- Easy to apply, low odour application
- Apply 2 coats in one day to reduce downtime
- New colour formulations to RAL shades
- Class 1 fire rating
- Tested safe for use in food production areas
- Superior performance demonstrated by ISO testing to CE mark EN1504-2

Need help? Speak to the experts

Our dedicated and professional team are here to help you get the best results for your project. They will talk you through the preparation and application stages when using **Safety Coat**.

Call our expert team on: 01483 418 418 (Weekdays 8:00am - 5:30pm. Saturday 9:00am - 12:00pm)



Safety Coat

Safety Coat Hygienic

Safety Coat Coarse

A two part epoxy with pre-blended aggregate for an even, easy clean, fine, anti slip finish

1 Surface Preparation

Bare Concrete – remove surface laitance, dust and any light dirt or grease deposits using Watco Etch & Clean. Watco Etch & Clean also etches smooth, bare concrete surfaces to provide a key. Remove Etch & Clean by thoroughly rinsing with clean water and allow surface to dry. If residual damp remains, this is acceptable since Safety Coat is breathable.

Powerfloated or very smooth surfaces – Watco Powerfloat Primer should be used on very smooth or power floated surfaces.

New Concrete – new concrete should be left for four weeks to dry in the summer and six in the winter. The surface should then be prepared using Watco Etch & Clean and thoroughly rinsed away and left to dry prior to applying this coating.

Painted surfaces – abrade to remove loose paint. Check remaining paint is well bonded. Very smooth, glossy paint should be lightly abraded to provide a key. Watco Bio-D can be used to remove grease and oil from painted surfaces.

Highly porous surfaces – a primer may be required for high suction surfaces such as sand and cement screed. Please contact us for advice.

2 Mixing

Remove the two inner tins from the tall outer tin. Stir the contents of each tin thoroughly and pour all of the contents into the outer tin (scrape around the inside of the tins to remove any residue). Mix the components together thoroughly using a spatula or similar wide bladed tool (a piece of wooden batten is ideal). Continue mixing until an even colour and consistency are obtained. Do not mix more than one pack at a time. If a paint stirrer fitted to an electric drill is used, also use the spatula to blend in any unmixed material from the sides and bottom of the tin.

3 Application

Best results are obtained in warm (minimum 15°C), dry conditions with good ventilation. In very high temperatures (30°C and above) it is recommended that bare concrete is lightly dampened first with water. Apply with a medium pile roller, working well into the surface of the concrete. Occasional stirring will ensure a more even distribution of the aggregate. Do not exceed the maximum coverage of 30m² per 5 litre pack, per coat. The product will darken slightly as curing commences and it should not be over rolled. The second coat can be applied as soon as the first coat is dry (generally 4-6 hours) and should be applied within 5 days. If more than 5 days elapse, the first coat should be lightly abraded before the second coat is applied. Avoid washing the surface for seven days.

4 Safety

All product labels provide general safety information. Material Safety Data Sheets are available. Food products must be removed from the area during application and cure.

5 Ordering

Available direct from Watco UK Limited and through agents worldwide. All Watco products are sold subject to the Company's Standard Conditions of Sale. The Company and its representatives are often asked to comment on potential uses of Watco products which differ from those described in the Company's data sheets. Whilst in such cases the Company and its representatives will always try to offer helpful and constructive advice, the Company cannot be held responsible for the results of such uses unless they are specifically confirmed in writing by Watco.

Safety Coat

Safety Coat Hygienic

Safety Coat Coarse

A two part epoxy with pre-blended aggregate for an even, easy clean, fine, anti slip finish

Specification

Composition	Anti slip water based epoxy resin.
Number of Components	1 x curing agent and 1 x resin.
Finish	Finely textured, mid gloss.
Primer Required	See 'Surface Preparation on p.2'.
Number of Coats	2
Dry Film Thickness	100 microns.
Wet Film Thickness	160 microns.
Usage Interior/Exterior	Interior. Can fade if used outside.
Application Tools	Medium pile roller. Cut in using brush.
Minimum Application Temperature	Air temperature 15°C Floor temperature 10°C
Suitable For	Concrete, sand and cement, wood, existing well bonded paint. The moisture content of concrete should be less than 75% RH.
Coverage	30m ² per 5L per coat.
Pot Life	Up to 2 hours at 20°C
Mix Ratio (by weight)	100 parts curing agent : 132 parts resin.
Cleaning Tools	Warm soapy water.
Shelf Life	12 months in unopened containers.
Cleaning	Normal industrial cleaners - Watco Bio-D is ideal. Do not steam clean.
Storage	Between 15°C - 25°C for at least 8 hours prior to use. Do not allow to freeze.
Principle Limitations	Unsuitable for bare metal.
Please contact us regarding applications not described here.	Most self levelling compounds cannot be painted - please ask for details.

Curing Time

	Recoat Time	Touch Dry	Light Traffic	Heavy Traffic	Full Chemical Resistance
10°C	6 - 8 hours	4 hours	16 hours	48 hours	7 days
20°C	4 - 6 hours	2 hours	12 hours	24 hours	7 days
30°C	4 hours	1 hour	12 hours	24 hours	7 days













Light Traffic: Foot, trolley, pallet truck, occasional forklift. Heavy Traffic: Regular forklift, heavy footfall, parked vehicles

Safety Coat






Safety Coat Hygienic

Safety Coat Coarse

Test Results

 Abrasion Resistance ISO 5470-1 Taber test method expresses results in mg on a scale between 0mg (highest resistance) and 3000mg (lowest). A reading below 3000mg is a CE mark pass.	3000mg —————> 0mg Lowest —————> Highest	 Flexibility ISO 1519 Flexibility is measured using a Mandral Flex Tester, 2mm is the most flexible, 36mm the least.	36mm —————> 2mm Lowest —————> Highest
 Impact Resistance ISO 6272 Impact is expressed as Newton metres. Greater than 4 Nm is a CE mark pass.	Class 1 >4Nm Class 2 >10Nm Class 3 >20Nm	 Gloss Value Rating is a 'Gloss Unit' measured on an Optical Glossmeter. Fine texture produces a mid-gloss finish on most substrates.	Matt 0-10%, Low Sheen 10-25%, Eggshell 26-40%, Semi-Gloss 41-69%, Gloss 70-85%, High Gloss +85%
 Scratch Resistance ISO 4586-2 Scratch resistance is measured using a Sclerometer and the resistance is measured in Newtons. 1N is the lowest resistance, 20N the highest.	1N —————> 20N Lowest —————> Highest	 Chemical Resistance Results shown are for tests with commonly used chemicals. Advice can be given for chemicals not listed here.	Petrol, diesel, fuel, methylated spirits, xylene, ammonia, white spirit, bleach, oil, anti-freeze, mineral hydraulic oil, caustic soda, detergents, sugar solutions. At 5%: citric acid.
 Surface Spread of Flame BS476 Part 7 The test measures the distance and time a flame takes to spread across a surface. Class 0 is the least combustible and Class 4 is the most combustible.	Class: 0 —> 1 —> 2 —> 3 —> 4 Least —————> Most Combustible Combustible	 Food Taint Test, Sensory Test Method (Also EN71/3 Non Toxic)	Safe for food production areas
 Adhesion Test EN 1542 Adhesion is expressed in MegaPascals (MPa) or Newton millimetres squared (Nmm ²). Greater than 2 MPa is a CE mark pass.	>2MPa (Nmm ²) = test pass	 Water Permeability EN 1062-3 To achieve a CE mark, the measurement must be less than 0.1 kg/m ² (24 h)0.5	CE Marking Critical Value: < 0.1kg/m ² /(24 h)0.5 W ₁ —————> W ₂ —————> W ₃ Lowest —————> Highest
 Wolff-Wilborn Hardness Test Also known as the 'pencil test', a 9H reading is the measure of a hardest coating, HB is the softest.	HB —————> 9H Least Hard —————> Hardest	 Slip Resistance BS7976-2 The Pendulum Test Value (PTV) is measured in wet conditions. A number above 36 indicates a 'low slip potential'.	High: 0-24 PTV Moderate: 25-35 PTV Low: 36+ PTV

Standard Compliance

 EN 1504-2 This mark indicates that a coating has passed all the tests required to carry a CE mark.	 BREEAM COMPLIANT	BREEAM COMPLIANT (for refurbishment)	 VOC LEVEL 30g/Litre LOW	VOC LEVEL	 ISO 16000 The 'Loi Grenelle' measurement of the effect of a product's VOC level within a building. A+ is the top safety rating.	ISO 16000	 REACH COMPLIANT	REACH COMPLIANT
---	---	--	--	------------------	--	------------------	--	----------------------------