

## EPOXY RESIN FLOOR PAINT & ANTI SLIP EPOXY RESIN FLOOR PAINT

Tough two-part floor paint

\*2.5L & 5L

(\*NOT pictured)



### AREAS OF USE

- Concrete floors in warehouses, production areas, garages, showrooms, etc.

### FEATURES

- Takes forklift traffic
- Good resistance to every day chemical spills
- Virtually odourless water-based formulation
- Mid sheen finish
- Easy application and clean up

### DESCRIPTION

Watco Basics Epoxy Floor Paint is a durable two-part paint suitable for medium to heavy use. It can be applied over existing well bonded paint, or onto bare concrete where it will penetrate the surface making it easier to keep clean. A separate unit of aggregate is supplied with Anti Slip Epoxy Resin Floor Paint, which is mixed into the paint to provide a finely textured slip resistant surface. Two roller applied coats will take heavy traffic including forklifts..

### COLOURS

Light Grey

Mid Grey

While great care is taken with the colour samples shown, no guarantee can be given that they represent exactly the colours offered.

### PREPARATION AND APPLICATION

#### 1. Prepare

- Clean and prepare bare concrete using Watco Etch & Clean. This will remove light grease and oil deposits.
- To remove heavier grease and oil use Watco Bio D. This can also be used to remove grease from existing paint.
- If over coating existing paint, please ensure it is well bonded. Remove any flaking or poorly bonded paint using a floor scraper for smaller areas or hire a grinder for larger areas. Smooth, glossy paint should be lightly abraded to provide a key.
- Make sure the surface is clean and dust free before continuing.
- New concrete should be at least 2 months old.
- This paint is water-based, so it doesn't matter if the floor remains slightly damp after cleaning.

#### 2. Repair

- Holes in excess of 5mm deep can be filled with Watco Basics Floor Repair Mortar, or providing the floor is level, Watco Pourable Repair Mortar.
- For repairs which need to be 'feather edged' to nothing, or for repairs to damaged joint edges, please refer to Watco Concrex® epoxy resin repair mortar. This should also be used if repairing broken kerb edges or step nosings.

#### 3. Painting

- Check the air temperature is around 15°C and the floor temperature at least 10°C.
- Stir the contents of the resin and curing agent tins and then empty the content of the resin into the curing agent tin.
- Mix the two components thoroughly using a wide bladed tool such as a piece of batten. A paint mixer in an electric drill is ideal.
- If using the 5L anti slip version follow the above instructions, but empty the tin of aggregate into the larger, curing agent tin and mix this thoroughly. Then empty the contents into a mixing pail (a plastic bucket is ideal) and add the contents of the resin tin. Just use half the tin of aggregate if you are using the 2.5L size.
- Mix thoroughly then tip the contents into a paint tray and apply using a medium pile roller. A brush can be used to cut in around edges.
- Now it is mixed you have up to 2 hours to apply it before it becomes unusable.
- Do not apply thickly.

#### Coverage

5L covers approximately 30m<sup>2</sup> with one coat depending on the texture and porosity of the floor. Two coats are recommended if using a roller. Coverage will be reduced if using a brush.

#### Clean up

Clean tools with water before the paint starts to dry.

#### Drying time

The paint dries best in warm, well ventilated conditions. There is a small amount of water in the formulation used to link the epoxy resin and curing agent. When it has done so, the water must evaporate, which is why good ventilation and a reasonable temperature are important.

Based on a temperature of 15°C - 20°C:

**Touch dry:** 10 hours

**Recoat:** 12 hours.

If more than 5 days pass between coats, the first coat will need to be lightly sanded to provide a key for the second.

**Light use:** 16-24 hours

**Cars:** 2-3 days

**Full chemical and scratch resistance:** 7 days

#### Limitations

- Avoid applying in cold (below 15°C) conditions, instead see Watco Cold Set Coating.
- Do not apply direct to dense, non-porous surfaces such as power floated concrete. This should first be coated with Watco Powerfloat Primer.
- May cause rusting if applied to bare metal.
- Unsuitable for outside application, (it will fade), instead use Watco Fastcoat.
- Avoid using in confined spaces with little or no ventilation since it won't dry. Choose Watco Epoxicoat™ High Build for such areas.

#### Storage

Avoid extremes of temperature.

#### Shelf life

24 months in unopened containers.

Material Safety Data Sheets are available on request.