

BITU-MEND® POUR & RESTORE

Pour on repairs for worn and damaged asphalt



AREAS OF USE

- Repairing shallow depressions, dished or pitted asphalt surfaces
- Car parks, yards, pavements

FEATURES

- Easy to mix and apply
- Ideal for shallow repairs
- Ready for traffic in 16 hours

Watco Bitu-Mend® Pour and Restore is ideal for shallow repairs to damaged or cracked asphalt and tarmac. Just mix and pour over pitted, cracked and damaged surfaces and it self smooths with just a little help from a trowel. The kit contains granite aggregate which is sprinkled over the repair to provide a slip resistant surface which blends in with the surrounding area.

SPECIFICATION

Composition	A blend of graded granite aggregate and epoxy resin.	Coverage	1.5m ² at 6.5mm or 1m ² at 10mm deep.
Finish	Granular, black, slip resistant surface.	Depth	6.5mm - 20mm. For deeper repairs see Watco Bitu-Mend® or Watco Bitu-Mend® Deep Fill.
Primer Required	A primer is not required when filling rough holes or cracks. We recommend Watco Tack Coat primer if using Watco Bitu-Mend® Deep Fill over smooth substrates.	Chemical Resistance	Good general resistance to many common such as diesel, petrol, etc. Please contact us for advice regarding other chemicals.
Number of Components	1 x resin and aggregate mix, 1 x curing agent, 1 x accelerator, finishing aggregate.	Curing Time	Touch dry in 1 hour at 20°C - 25°C, ready for traffic in 16 hours at 20°C - 25°C.
Usage Interior/ Exterior	Exterior & interior.	Pot Life	Working life of mixed components: Approximately 15 minutes at 20°C, less in higher temperatures.
Application Tools	Trowel.	Shelf Life	24 months in unopened container.
Suitable For	Asphalt, tarmac.	Storage	Store above 10°C. Do not allow to freeze.
Pack Size	15kg		

PREPARATION & APPLICATION

SURFACE PREPARATION

Ensure the void to be filled is clean, dry (slight damp is acceptable) and sound.

MIXING

Pour the tins of Curing Agent and Accelerator onto the Resin and aggregate mix in the outer bucket.

Please note – If you are repairing a number of small areas and need to extend the working life of the mixed product, or if the temperature is above 23°C, DO NOT USE the Accelerator. Use a wide bladed tool to ensure thorough mixing.

APPLICATION

Pour the mixed product onto the damaged asphalt and spread out using a trowel. The product will self-smooth to a level finish. Before the Bitu-Mend Pour & Restore cures, sprinkle the finishing aggregate over the repair.

SAFETY

All product labels provide general safety information. Material Safety Data Sheets are available. Food products must be removed from the area during application and cure.



WATCO.CO.UK