

BITU-MEND® ADVANCED

For the strongest ever asphalt repairs

AREAS OF USE

- Potholes in asphalt and tarmac
- Gangways and work areas
- Car parks and loading bays where forklifts and lorries operate
- Splits and cracks in asphalt
- Roller shutter door guide rails



FEATURES

- Cures to a hard, black, slip resistant finish
- Can be applied at any thickness from 10mm -100mm
- Can also be used on concrete
- Ready for use in 12 hours

DESCRIPTION

Watco Bitu-Mend® Advanced is ideal for filling holes in asphalt and similar type floors. The epoxy resin formulation is much stronger and longer lasting than traditional bitumen based products. It's strength allows for thinner repairs than conventional products and it is ideal for heavily trafficked areas. It has good general resistance to many chemicals commonly found in Industry. Please contact us for advice regarding other chemicals.

SPECIFICATION

Composition	A blend of graded granite aggregate and epoxy resin.
Number of Components	1 x resin, 1 x curing agent, 1 x aggregate.
Finish	Granular, black, slip resistant surface.
Primer required	No. We recommend Watco Tack Coat primer if using over smooth substrates.
Usage Interior/ Exterior	Exterior and interior.
Application Tools	Trowel.
Suitable For	Concrete, sand & cement, asphalt, tarmac.
Pack Size	25kg
Coverage	Approximately 1m ² at 15mm thick.

COLOUR



Pot life	Working life of mixed components: Approximately 30 minutes at 10°C - 20°C, less in higher temperatures..
Curing	Can be walked on after 8 -12 hours and subject to heavy traffic after 12 - 24 hours (all at 10°C - 20°C). Lower temperatures will extend the curing time.
Shelf Life	12 months in unopened containers.
Storage	Store above 10°C.
Safety.	All product labels provide general safety information. Material Safety Data Sheets are available. Food products must be removed from the area during application and cure.

PREPARATION & APPLICATION

SURFACE PREPARATION

Ensure the void to be filled is clean, dry (slight damp is acceptable) and sound.

MIXING

Mixing is easier on a board, but it can be done in the plastic container provided. Empty the contents of the smaller curing agent tin into the larger resin tin and mix thoroughly using a palette knife or similar wide bladed tool. Immediately empty the mixed components onto the granite aggregate. Mix using a trowel to achieve a loose textured black compound. Ensure that the dry aggregate is thoroughly coated.

APPLICATION

Tip the mixed product into the void and work into any gaps and crevices with a trowel. Lightly tamp down with a piece of wood, compacting the product to remove air pockets. Finish with a trowel.

SAFETY

Material Safety Data Sheets are available.



WATCO.CO.UK